Page 1/13

## Safety data sheet

according to 1907/2006/EC, Article 31

Printing date 17.02.2022

Version number 42

Revision: 05.05.2021

## SECTION 1: Identification of the substance/mixture and of the company/ undertaking

· 1.1 Product identifier

- · Trade name: Union AIMg 4,5 Mn
- · CAS Number: -
- · EINECS Number: -
- **1.2 Relevant identified uses of the substance or mixture and uses advised against** No further relevant information available.
- Application of the substance / the mixture
   Rods and Wires for Welding
   The product is a manufactured article in the sense of Article 3 No. 3, 1907/2006/EC (REACh). The purpose of the
   present safety data sheet is therefore to provide instruction on safe usage of the product.
- · 1.3 Details of the supplier of the safety data sheet
- · Manufacturer/Supplier:

voestalpine Böhler Welding Germany GmbH Hafenstr. 21 59067 Hamm, Germany www.voestalpine.com/welding

· Further information obtainable from:

Research and Development Helena Stabel +49 2381 271 - 578; Helena.Stabel@voestalpine.com

· 1.4 Emergency telephone number:

NCEC

+44 1235 239670

- **SECTION 2: Hazards identification**
- · 2.1 Classification of the substance or mixture
- Classification according to Regulation (EC) No 1272/2008
   The Product does not meet the criteria for classification in any hazard class according to Regulation (EC) No
  1272/2008 on classification, labelling and packaging of substances and mixtures.
- · 2.2 Label elements
- · Labelling according to Regulation (EC) No 1272/2008 Void
- · Hazard pictograms Void
- · Signal word Void
- · Hazard statements Void
- · 2.3 Other hazards
- · Results of PBT and vPvB assessment
- · PBT: Not applicable.
- · vPvB: Not applicable.

(Contd. on page 2)

EU

Page 2/13

## Safety data sheet

according to 1907/2006/EC, Article 31

Printing date 17.02.2022

Version number 42

Revision: 05.05.2021

(Contd. of page 1)

Trade name: Union AIMg 4,5 Mn

3.2 Chemical characterisation Description: Mixture of substance	<b>: Mixtures</b> es listed below with nonhazardous additions.	
Dangerous components:		
CAS: 7429-90-5 EINECS: 231-072-3 Index number: 013-001-00-6 Reg.nr.: 01-2119529243-45-XXXX	aluminium	50-100%
CAS: 7439-95-4 EINECS: 231-104-6 Index number: 012-001-00-3 Reg.nr.: 01-2119537203-49-XXXX	magnesium powder (pyrophoric) Flam. Sol. 1, H228; Water-react. 2, H261	5-12.5%
CAS: 7439-96-5 EINECS: 231-105-1 Reg.nr.: 01-2119449803-34-XXXX	manganese substance with a Community workplace exposure limit	0.1-2.5%

## SECTION 4: First aid measures

- **4.2 Most important symptoms and effects, both acute and delayed** No further relevant information available.
- · General information: No special measures required.
- · After inhalation: Supply fresh air; consult doctor in case of complaints.
- After skin contact: Generally the product does not irritate the skin.
- · After eye contact: Rinse opened eye for several minutes under running water.
- · After swallowing: Seek medical treatment.
- **4.3 Indication of any immediate medical attention and special treatment needed** No further relevant information available.

#### **SECTION 5: Firefighting measures**

- · 5.1 Extinguishing media
- · Suitable extinguishing agents: Suitable to surrounding conditions.
- · 5.2 Special hazards arising from the substance or mixture No further relevant information available.
- 5.3 Advice for firefighters

For deletion of fire just use dry powders. Don't use any water or halogenated containing extinguishing agents • **Protective equipment:** No special measures required.

**Frotective equipment.** No special measures required.

## SECTION 6: Accidental release measures

• 6.1 Personal precautions, protective equipment and emergency procedures Ensure adequate ventilation

Use respiratory protective device against the effects of fumes/dust/aerosol.

- · 6.2 Environmental precautions: Do not allow to enter sewers/ surface or ground water.
- · 6.3 Methods and material for containment and cleaning up: Pick up mechanically.
- 6.4 Reference to other sections

See Section 7 for information on safe handling.

(Contd. on page 3)

EU

## voestalpine Böhler Welding

Page 3/13

## Safety data sheet

according to 1907/2006/EC, Article 31

Printing date 17.02.2022

Version number 42

Revision: 05.05.2021

(Contd. of page 2)

Trade name: Union AIMg 4,5 Mn

See Section 8 for information on personal protection equipment. See Section 13 for disposal information.

## SECTION 7: Handling and storage

- 7.1 Precautions for safe handling Ensure that suitable extractors are available on processing machines • Information about fire - and explosion protection: No special measures required.
- · 7.2 Conditions for safe storage, including any incompatibilities
- · Storage:
- · Requirements to be met by storerooms and receptacles: No special requirements.
- · Information about storage in one common storage facility: Not required.
- · Further information about storage conditions: None.
- · 7.3 Specific end use(s) No further relevant information available.

#### SECTION 8: Exposure controls/personal protection

- · 8.1 Control parameters
- · Ingredients with limit values that require monitoring at the workplace:
- 7439-96-5 manganese

IOELV Long-term value: 0.2\* 0.05\*\* mg/m<sup>3</sup> as Mn; \*inhalable, \*\*respirable fraction

· Additional information: The lists valid during the making were used as basis.

- · 8.2 Exposure controls
- Personal protective equipment:
- · General protective and hygienic measures: Wash hands before breaks and at the end of work.
- · Respiratory protection: Filter P2
- **Protection of hands:** EN 12477

Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation

- Material of gloves Leather gloves
- Penetration time of glove material

The exact break through time has to be found out by the manufacturer of the protective gloves and has to be observed.

- Eye protection: Safety glasses
- · Body protection: Protective work clothing

## **SECTION 9: Physical and chemical properties**

- $\cdot$  9.1 Information on basic physical and chemical properties
- General Information
- · Appearance:
- Form:
- Colour:
- · Odour:
- · Odour threshold:

Solid Not determined. Odourless Not determined.

(Contd. on page 4)

## voestalpine Böhler Welding

Page 4/13

## Safety data sheet

according to 1907/2006/EC, Article 31

Printing date 17.02.2022

Version number 42

Revision: 05.05.2021

#### Trade name: Union AIMg 4,5 Mn

	(Contd. of page
pH-value:	Not applicable.
Flash point:	Not applicable.
Flammability (solid, gas):	Not determined.
Decomposition temperature:	Not determined.
Auto-ignition temperature:	Product is not selfigniting.
Explosive properties:	Product does not present an explosion hazard.
Explosion limits:	
Lower:	Not determined.
Upper:	Not determined.
Density:	Not determined.
Relative density	Not determined.
Vapour density	Not applicable.
Evaporation rate	Not applicable.
water:	Insoluble.
Partition coefficient: n-octanol/	water: Not determined.
Dynamic:	Not applicable.
Kinematic:	Not applicable.
Solvent separation test:	
Solids content:	100.0 %
9.2 Other information	No further relevant information available.

## SECTION 10: Stability and reactivity

- · 10.1 Reactivity No further relevant information available.
- · 10.2 Chemical stability
- · Thermal decomposition / conditions to be avoided:
- No decomposition if used and stored according to specifications.
- · 10.3 Possibility of hazardous reactions No dangerous reactions known.
- · 10.4 Conditions to avoid No further relevant information available.
- · 10.5 Incompatible materials: No further relevant information available.
- · 10.6 Hazardous decomposition products: No dangerous decomposition products known.

## **SECTION 11: Toxicological information**

- · 11.1 Information on toxicological effects
- · Acute toxicity Based on available data, the classification criteria are not met.
- · Primary irritant effect:
- · Skin corrosion/irritation Based on available data, the classification criteria are not met.
- · Serious eye damage/irritation Based on available data, the classification criteria are not met.
- · Respiratory or skin sensitisation Based on available data, the classification criteria are not met.
- · Additional toxicological information:
- · Repeated dose toxicity
- · Germ cell mutagenicity Based on available data, the classification criteria are not met.

(Contd. on page 5)

## voestalpine Böhler Welding

Page 5/13

## Safety data sheet

according to 1907/2006/EC, Article 31

Printing date 17.02.2022

Version number 42

Revision: 05.05.2021

Trade name: Union AIMg 4,5 Mn

- · Carcinogenicity Based on available data, the classification criteria are not met.
- · Reproductive toxicity Based on available data, the classification criteria are not met.
- · STOT-single exposure Based on available data, the classification criteria are not met.
- STOT-repeated exposure Based on available data, the classification criteria are not met.
- · Aspiration hazard Based on available data, the classification criteria are not met.

#### **SECTION 12: Ecological information**

- · 12.1 Toxicity
- · Aquatic toxicity: No further relevant information available.
- · 12.2 Persistence and degradability No further relevant information available.
- · 12.3 Bioaccumulative potential No further relevant information available.
- 12.4 Mobility in soil No further relevant information available.
- · Additional ecological information:
- · General notes: Water hazard class 1 (German Regulation) (Self-assessment): slightly hazardous for water
- · 12.5 Results of PBT and vPvB assessment
- · PBT: Not applicable.
- · vPvB: Not applicable.
- · 12.6 Other adverse effects No further relevant information available.

#### **SECTION 13: Disposal considerations**

- · 13.1 Waste treatment methods
- · Recommendation Must be specially treated adhering to official regulations.
- · European waste catalogue
- 12 01 13 welding wastes
- 12 01 20\* spent grinding bodies and grinding materials containing hazardous substances

12 01 04 non-ferrous metal dust and particles

Uncleaned packaging:

· Recommendation: Disposal must be made according to official regulations.

SECTION 14: Transport information	ion	
· 14.1 UN-Number	Void	
· ADR, ADN, IMDG, IATA	- Void	
<ul> <li>· 14.2 UN proper shipping name</li> <li>· ADR, ADN, IMDG, IATA</li> </ul>	Void	
· 14.3 Transport hazard class(es)		
· ADR, ADN, IMDG, IATA · Class	Void	
· 14.4 Packing group · ADR, IMDG, IATA	Void	
		(Contd. on page 6)

(Contd. of page 4)

Page 6/13

## Safety data sheet

according to 1907/2006/EC, Article 31

Printing date 17.02.2022

Version number 42

Revision: 05.05.2021

Trade name: Union AIMg 4,5 Mn

	(Contd. of page
<ul> <li>14.5 Environmental hazards:</li> <li>Marine pollutant:</li> </ul>	No
· 14.6 Special precautions for user	Not applicable.
<ul> <li>14.7 Transport in bulk according to Annex Marpol and the IBC Code</li> </ul>	ll of Not applicable.
· Transport/Additional information:	Not dangerous according to the above specifications.
· UN "Model Regulation":	- Void

## **SECTION 15: Regulatory information**

· 15.1 Safety, health and environmental regulations/legislation specific for the substance or mixture

No further relevant information available.

- · Directive 2012/18/EU
- · Named dangerous substances ANNEX I None of the ingredients is listed.
- DIRECTIVE 2011/65/EU on the restriction of the use of certain hazardous substances in electrical and electronic equipment – Annex II

None of the ingredients is listed.

· REGULATION (EU) 2019/1148

 Annex I - RESTRICTED EXPLOSIVES PRECURSORS (Upper limit value for the purpose of licensing under Article 5(3))

None of the ingredients is listed.

· Annex II - REPORTABLE EXPLOSIVES PRECURSORS

7429-90-5 aluminium

· Regulation (EC) No 273/2004 on drug precursors

None of the ingredients is listed.

 Regulation (EC) No 111/2005 laying down rules for the monitoring of trade between the Community and third countries in drug precursors

None of the ingredients is listed.

· 15.2 Chemical safety assessment: A Chemical Safety Assessment has not been carried out.

## **SECTION 16: Other information**

This information is based on our present knowledge. However, this shall not constitute a guarantee for any specific product features and shall not establish a legally valid contractual relationship.

#### · Additional information:

Recommendations for exposure scenarios, measures for risk management and identification of working conditions under which metals, metal alloys and products made of metal can be safely worked can be found attached. Detailed information can be found on our webpage www.voestalpine.com (Environment, REACH at voestalpine).

(Contd. on page 7)

Page 7/13

# Safety data sheet according to 1907/2006/EC, Article 31

Printing date 17.02.2022

Version number 42

Revision: 05.05.2021

Trade name: Union AIMg 4,5 Mn

	(Contd. of page 6)
European Welding Association       Welding Exposure Scenario WES - ENGL         Doc -5-2021       Doc -5-2021         Page 1 of 6       Page 1 of 6	
Guidance and Recommendations for Exposure Scenarios, Risk Management Measures and to identify Operational Conditions under which metals, alloys and metallic articles and mixtures may be safely welded regarding welding fumes and gases exposure	
Welding/Brazing produces fumes, which can affect human health.	
Welding and allied processes generate a varying mixture of fumes (airborne particles) and gases, which, if inhaled or swallowed, constitute a health hazard:	
The degree of risk will depend on the composition of the fume, the concentration of the fume and duration of exposure.	
The fume composition is dependent upon the material being worked, the process and consumables being used, coatings on the work such as paint, galvanizing or plating, oil or contaminants from cleaning and degreasing activities.	
The amount of fumes generated is dependent on the welding process, the welding parameters, the shielding gas, the type of consumable and the potential coating on the work.	
A systematic approach to the assessment of exposure is necessary, taking into account the particular circumstances for the operator and ancillary worker that can be exposed.	
General Rules to reduce exposure to welding fumes and gases	
The employer shall ensure that the risk from welding fumes to the safety and health of workers is eliminated or reduced to a minimum. Start every new work with an Occupational Safety & Health Risk Inventory.	
The following principles shall be applied, unless local regulation say otherwise: <b>1.</b> Substitution: Select the applicable process/base material combinations with the lowest emission, whenever possible Set welding process with the lowest emission parameters (e.g. welding parameters/arc mode	
<ul> <li>transfer, shielding gas composition) *</li> <li><b>Technological Means:</b></li> <li>Apply the relevant collective protective measures (general ventilation, local exhaust ventilation) in</li> </ul>	
accordance with class number. <b>3.</b> Organizational Measures: Limit the time a worker is exposed to welding fumes,	
Establish and apply Welding Procedure Specifications <b>4.</b> <i>Personal Protective Equipment:</i> To protect the worker, wear the relevant personal protective equipment in accordance with the duty cycle	
In addition, compliance with the National Regulations regarding the exposure of welders and related personnel to welding fumes, their components with specific occupational exposure limit, and gaseous substances with specific occupational exposure limits shall be verified. It is therefore strongly recommended to seek clarification of specific national legislation that may apply.	
* In MIG / MAG process, innovative waveform controlled processes generate less welding fumes and particles than conventional processes - The use of such processes can be an additional measure to reduce the exposure of the welder and or workers	
	(Contd. on page 8

Page 8/13

# Safety data sheet according to 1907/2006/EC, Article 31

Printing date 17.02.2022

Version number 42

Revision: 05.05.2021

Trade name: Union AIMg 4,5 Mn

							(Contd. of p	
_	_	_						
			Welding Expo	sure Scenario WE	S - ENGL			
					Doc -5-2021			
Europ	ean Welding Asso	ciation			Page 2 of 6			
Risk Ma	nagement Measures fo	r Individual pro	ocess/base material con	nbinations				
Accordin	ng to the welding or	allied process	and the base materia	I to be welded, a general	guidance on			
Technolo An appr allied pr The indi	ogical means is propos oximate ranking to mit ocess/base material co	ed in the table b igate the risk of mbination. aterial combina	below. Welding fumes and ga	ses exposure is given for ea	ch welding or			
-			IIW) assessed the publi	cation of IARC Monograph :	118 Based on			
the curr	ent state of knowledg	e, IIW confirms	s its statement from 2	011 on "Lung cancer and	welding" and			
				ne to a minimum. It also reco ers must ensure that exposu				
				s posted both on IIW and EV				
For eac	h class general reco	mmendations	on Ventilation/Extrac	tion/Filtration and Person	al Protection			
	ent are proposed.	innenducions	on ventilation/extrac	dony mitration and reison				
	Process			Ventilation /	PPE <sup>2</sup>	PPE <sup>2</sup>		
Class <sup>1</sup>	Process (according to ISO 4063)	Base Materials	Remarks	Extraction / Filtration <sup>14</sup>	DC<15%	DC>15%		
1	GTAW		Non-confined space <sup>1</sup>	6	1			
	141	- - - All	All Except Aluminum					
	SAW 12			GV low <sup>3</sup>				
	Autogenous							
	PAW							
	15							
	ESW/EGW 72/73				n.r.	n.r.		
	Resistance							
	2 Stud welding							
	78 Solid state							
	521							
		All	Except Cd- alloys	GV low <sup>3</sup>	n.r.	n.r.		
11	521 Gases Brazing 9 GTAW	Second An						
199	521 Gases Brazing 9 GTAW 141	All Aluminum	n.a.	GV low <sup>3</sup> GV medium <sup>4</sup>	n.r. n.a.	n.r. FFP2 <sup>5</sup>		
II III	521 Gases Brazing 9 GTAW	Second An	n.a. Except Be-, V- , Mn-, Ni- alloys and					
199	521 Gases Brazing 9 GTAW 141 MMAW 111 FCAW	Aluminum	n.a. Except Be-, V- , Mn-, Ni- alloys and Stainless <sup>6</sup> Except Stainless and	GV medium <sup>4</sup>	n.a.			
199	521 Gases Brazing 9 GTAW 141 MMAW 111 FCAW 136/137	Aluminum All All	n.a. Except Be-, V- , Mn-, Ni- alloys and Stainless <sup>6</sup> Except Stainless and Ni- alloys <sup>6</sup>	GV medium <sup>4</sup> GV low <sup>7</sup>	n.a.			
199	521 Gases Brazing 9 GTAW 141 MMAW 111 FCAW 136/137 GMAW 131/135	Aluminum	n.a. Except Be-, V-, Mn-, Ni- alloys and Stainless <sup>6</sup> Except Stainless and Ni- alloys <sup>6</sup> Except Cu-, Be-, V- alloys <sup>6</sup>	GV medium <sup>4</sup>	n.a.	FFP2 <sup>5</sup>		
199	521 Gases Brazing 9 GTAW 141 MMAW 111 FCAW 136/137 GMAW	Aluminum All All	n.a. Except Be-, V-, Mn-, Ni- alloys and Stainless* Except Stainless and Ni- alloys* Except Cu-, Be-, V- alloys* Except Be-, V-, Cu-, Mn-, Ni-alloys and	GV medium <sup>4</sup> GV low <sup>7</sup>	n.a.	FFP2 <sup>5</sup>		
199	521           Gases Brazing         9           GTAW         141           MMAW         111           FCAW         136/137           GMAW         131/135           Powder Plasma Arc         152           All processes class I         1	Aluminum All All All All All Painted / primed / oiled / galvanized	n.a. Except Be-, V-, Mn-, Ni- alloys and Stainless <sup>6</sup> Except Stainless and Ni- alloys <sup>6</sup> Except Cu-, Be-, V- alloys <sup>6</sup>	GV medium <sup>4</sup> GV low <sup>7</sup>	n.a. Improved heimet <sup>re</sup>	FFP2 <sup>5</sup> FFP2 <sup>5</sup>		
Ш	521 Gases Brazing 9 GTAW 141 MMAW 111 FCAW 136/137 GMAW 131/135 Powder Plasma Arc 152	Aluminum All All All All All Primed / oiled / galvanized Painted / Painted /	n.a. Except Be-, V-, Mn-, Ni-alloys and Stainless <sup>4</sup> Except Stainless and Ni-alloys <sup>4</sup> Except Cu-, Be-, V-, alloys <sup>4</sup> Except Be-, V-, Cu-, Mn-, Ni-alloys and Stainless <sup>4</sup> No Pb containing	GV medium <sup>4</sup> GV low <sup>7</sup> LEV low <sup>12</sup>	n.a.	FFP2 <sup>5</sup>		
Ш	521           Gases Brazing           9           GTAW           141           MMAW           111           FCAW           136/137           GMAW           131/135           Powder Plasma Arc           152           All processes class I           All processes class III           MMAW	Aluminum All All All All All Painted / primed / oiled / galvanized Painted / Painted / Painted / Staintess, Ni-,	n.a. Except Be-, V-, Mn-, Ni- alloys and Stainless <sup>4</sup> Except Stainless and Ni- alloys <sup>6</sup> Except Cu-, Be-, V- alloys <sup>4</sup> Except Cy-, Cu-, Mn-, Ni-alloys and Stainless <sup>6</sup> No Pb containing primer	GV medium <sup>4</sup> GV low <sup>7</sup> LEV low <sup>12</sup> GV low <sup>3</sup>	n.a. Improved heimet <sup>re</sup>	FFP2 <sup>5</sup> FFP2 <sup>5</sup> FFP3 <sup>8</sup> , TH2/P2,		
III IV	521       Gases Brazing       9       GTAW       141       MMAW       111       FCAW       136/137       GMAW       131/135       Powder Plasma Arc       152       All processes class I       All processes class III	Aluminum All All All All Painted / primed / oiled / galvanized Painted / primed / oiled / galvanized Stainless, Ni-, Be-, and Vi-	n.a. Except Be-, V-, Mn-, Ni- alloys and Stainless <sup>4</sup> Except Stainless and Ni- alloys <sup>6</sup> Except Cu-, Be-, V- alloys <sup>4</sup> Except Cy-, Cu-, Mn-, Ni-alloys and Stainless <sup>6</sup> No Pb containing primer	GV medium <sup>4</sup> GV low <sup>7</sup> LEV low <sup>12</sup> GV low <sup>3</sup>	n.a. Improved heimet <sup>re</sup>	FFP2 <sup>5</sup> FFP2 <sup>5</sup> FFP3 <sup>8</sup> , TH2/P2,		
III IV	521           Gases Brazing           GTAW           141           MMAW           111           FCAW           136/137           GMAW           131/135           Powder Plasma Arc           152           All processes class I           MMAW           111           FCAW	Aluminum All All All All Painted / olled / primed / olled / galvanized Stainless, Ni-, Be-, and V- alloys Stainless, Mr-	n.a. Except Be-, V-, Mn-, Ni- alloys and Stainless <sup>4</sup> Except Stainless and Ni- alloys <sup>6</sup> Except Cu-, Be-, V- alloys <sup>4</sup> Except Cy-, Cu-, Mn-, Ni-alloys and Stainless <sup>6</sup> No Pb containing primer	GV medium <sup>4</sup> GV low <sup>7</sup> LEV low <sup>12</sup> GV low <sup>3</sup>	n.a. Improved heimet <sup>re</sup>	FFP2 <sup>5</sup> FFP2 <sup>5</sup> FFP3 <sup>8</sup> , TH2/P2,		
III IV	521           Gases Brazing           9           GTAW           141           MMAW           111           FCAW           736/37           GMAW           131/136           Powder Plasma Arc           152           All processes class I           All processes class III           MMAW           111	Aluminum All All All All All Painted / primed / oiled / galvanized Painted / primed / oiled / galvanized Stainless, Ni-, Be-, and V- alloys Stainless, Mo- alloys	n.a. Except Be-, V-, Mn-, Ni- alloys and Stainless <sup>4</sup> Except Stainless and Ni- alloys <sup>6</sup> Except Cu-, Be-, V- alloys <sup>4</sup> Except Cy-, Cu-, Mn-, Ni-alloys and Stainless <sup>6</sup> No Pb containing primer	GV medium <sup>4</sup> GV low <sup>7</sup> LEV low <sup>12</sup> GV low <sup>3</sup>	n.a. Improved heimet <sup>14</sup> FFP2 <sup>8</sup> TH3/P3,	FFP2* FFP2* FFP2* TH2/P2, or LDH3 TH3/P3,		
III IV	521 Gases Brazing 9 GTAW 141 MMAW 1111 FCAW 136/137 GMAW 131/135 Powder Plasma Arc 152 All processes class I All processes class III MMAW 111 FCAW 136/137 GMAW 131	Aluminum All All All All All Painted / primed / oiled / galvanized galvanized Staintess, Nin- alloys Stainess, Mn- and Ni-alloys Cu-alloys	n.a. Except Be-, V-, Mn-, Ni- alloys and Stainless <sup>6</sup> Except Cu-, Be-, V alloys <sup>6</sup> Except Cu-, Be-, V alloys <sup>6</sup> Except Cu-, Be-, V alloys <sup>6</sup> Except Cu-, Be-, V Stainless <sup>6</sup> No Pb containing primer No Pb containing primer	GV low <sup>7</sup> LEV low <sup>2</sup> GV low <sup>3</sup> GV low <sup>3</sup>	n.a. Improved helmet <sup>16</sup>	FFP2 <sup>s</sup> FFP2 <sup>s</sup> FFP3 <sup>s</sup> , TH2/P2, or LDH3		
III IV	521 Gases Brazing 9 GTAW 141 MMAW 111 FCAW 136/137 GMAW 131/135 Powder Plasma Arc 152 All processes class I All processes class III All processes class III MMAW 111 FCAW 136/137 GMAW	Aluminum All All All All All Painted / primed / oiled / galvanized Painted / primed / oiled / galvanized Stainless, Ni-, Be-, and V- alloys Stainless, Mo- alloys	n.a. Except Be-, V-, Mn-, Ni- alloys and Stainless <sup>6</sup> Except Cu-, Be-, V alloys <sup>6</sup> Except Cu-, Be-, V alloys <sup>6</sup> Except Cu-, Be-, V alloys <sup>6</sup> Except Cu-, Be-, V Stainless <sup>6</sup> No Pb containing primer No Pb containing primer	GV low <sup>7</sup> LEV low <sup>2</sup> GV low <sup>3</sup> GV low <sup>3</sup>	n.a. Improved heimet <sup>14</sup> FFP2 <sup>8</sup> TH3/P3,	FFP2* FFP2* FFP2* TH2/P2, or LDH3 TH3/P3,		

(Contd. on page 9) - EU

Page 9/13

# Safety data sheet according to 1907/2006/EC, Article 31

Printing date 17.02.2022

Version number 42

Revision: 05.05.2021

#### Trade name: Union AIMg 4,5 Mn

Europ	European Welding Association Welding Exposure Scenario WES - ENGL Doc -5-2021 Page 3 of 6							
Class <sup>1</sup>	Process (according to ISO 4063)	Base Materials	Remarks Non-confined spa	Ventilation / Extraction / Filtration <sup>14</sup>	PPE <sup>2</sup> DC<15%	PPE <sup>2</sup> DC>15%		
VI	GMAW 131 Powder Plasma Arc 152	Be-, and V- alloys	n.a.	Reduced (negative) pressured area <sup>9</sup> LEV low <sup>12</sup>	TH3/P3, LDH3 <sup>11</sup>	TH3/P3, LDH3 <sup>11</sup>		
VII	Self shielded FCAW 114 Self-shielded FCAW	Un-, high alloyed steel Un-, high	Cored wire, not containing Ba Cored wire,	Reduced (negative) pressured area <sup>9</sup> LEV medium <sup>13</sup>				
	114 All	alloyed steel Painted / primed / galvanized	containing Ba Paint / Primer containing Pb		TH3/P3, LDH3 <sup>11</sup>			
	Arc Gouging and Cutting 8 Thermal Spray	All	n.a.	Reduced (negative) pressured area <sup>9</sup> LEV high <sup>10</sup>		TH3/P3, LDH3 <sup>11</sup>		
	Thermal Spray Gases Brazing 9	Cd- alloys	n.a. n.a.	-				
1	Laser Welding	Clo	sed system or Confin	ed space <sup>15</sup>				
	52 Laser Cutting 84 Electron Beam	All	Closed system	GV medium⁴	n.a.	n.a.		
VIII	51 All	All	Confined space	LEV high <sup>10</sup> External air supply	LDH3 <sup>11</sup>	LDH3 <sup>11</sup>		
	Filtrating half mask (FFP3 Reduced (negative) pres surrounded area, is mair Local Exhaust Ventilatior Helmet with powered fil Local Exhaust Ventilatior Recommended measure ept unalloyed steel and alum A confined space, despit	Medium (double of 2) able is used, meas Low. When no Loo 3), helmet with powe sured Area: A sepa trained (LEV) High, extract (LEV) High, extract or (LEV) Holdium, ex s to comply with hinum, shall be filte e its name, is not it	compared to Low) sures from "Class V" a lal Exhaust Ventilation ared filters (TH2/P2), c irrate, ventilated area tion at source (include tion at source (include traction	re required 1, the ventilation requirement is 5-fo r helmet with extenal air supply (LDF where reduced (negative) pressure, es table, hood, arm or torch extracti r supply (LDH3) es table, hood, arm or torch extracti ludes table, hood, arm or torch extraction to any torch extracted fumes, for the outside environment. mples of confined spaces include sh	i2) compared t on) action) all material	ls		
The follo	tional Standards & EU I owing ISO standards an re to welding fumes and	d European Unio		s general information for risk ass	essments c	of		

Page 10/13

# Safety data sheet according to 1907/2006/EC, Article 31

Printing date 17.02.2022

Version number 42

Revision: 05.05.2021

Trade name: Union AIMg 4,5 Mn

Image: Solution in the state of the sta
ISO EN 21904-1:2020       Health and safety in welding and allied processes Equipment for capture and separation of welding fume Part 1: General requirements         ISO EN 21904-2:2020       Health and safety in welding and allied processes Equipment for capture and separation of welding fume Part 2: Requirements for testing and marking o separation efficiency         ISO EN 21904-3:2018       Health and safety in welding and allied processes Requirements, testing and marking of equipment for air filtration Part 3: Determination of the capture efficiency of on-torch welding fume extraction devices         ISO EN 21904-4:2020       Health and safety in welding and allied processes Equipment for capture and separation of welding fume Part 4: Determination of the minimum air volume flow rate of capture devices         ISO EN 21904-4:2020       Health and safety in welding and allied processes Equipment for capture and separation of welding fume Part 4: Determination of the minimum air volume flow rate of capture devices         ISO 15607:2003       Specification and qualification of welding procedures for metallic materials Generatures         EN ISO 15609:       Specification and qualification of welding procedures for metallic materials - Welding
SO EN 21904-2:2020       Health and safety in welding and allied processes Equipment for capture and separation of welding fume Part 2: Requirements for testing and marking or separation efficiency         SO EN 21904-3:2018       Health and safety in welding and allied processes Requirements, testing and marking of equipment for air filtration Part 3: Determination of the capture efficiency of on-torch welding fume extraction devices         SO EN 21904-4:2020       Health and safety in welding and allied processes Equipment for capture and separation of welding fume Part 4: Determination of the minimum air volume flow rate of capture devices         SO EN 21904-4:2020       Health and safety in welding and allied processes Equipment for capture and separation of welding fume Part 4: Determination of the minimum air volume flow rate of capture devices         SO EN 21904-3:2013       Specification and qualification of welding procedures for metallic materials Generatives         SO EN 21904-4:2020       Specification and qualification of welding procedures for metallic materials Generatives
separation of welding fume Part 2: Requirements for testing and marking or separation efficiency         ISO EN 21904-3:2018       Health and safety in welding and allied processes Requirements, testing and marking of equipment for air filtration Part 3: Determination of the capture efficiency of on-torch welding fume extraction devices         ISO EN 21904-4:2020       Health and safety in welding and allied processes Equipment for capture and separation of welding fume Part 4: Determination of the minimum air volume flow rate of capture devices         ISO 15607:2003       Specification and qualification of welding procedures for metallic materials Generar rules         EN ISO 15609:       Specification and qualification of welding procedures for metallic materials - Welding
marking of equipment for air filtration — Part 3: Determination of the capture efficiency of on-torch welding fume extraction devices         ISO EN 21904-4:2020       Health and safety in welding and allied processes — Equipment for capture and separation of welding fume Part 4: Determination of the minimum air volume flow rate of capture devices         ISO 15607:2003       Specification and qualification of welding procedures for metallic materials — Generar rules         EN ISO 15609:       Specification and qualification of welding procedures for metallic materials - Welding
separation of welding fume Part 4: Determination of the minimum air volume flov rate of capture devices ISO 15607:2003 Specification and qualification of welding procedures for metallic materials Genera rules EN ISO 15609: Specification and qualification of welding procedures for metallic materials - Welding
EN ISO 15609: Specification and qualification of welding procedures for metallic materials - Welding
procedure specification part1 -> part 6
ISO 17916:2016 Safety of thermal cutting machines
EN 149:2001+A1:2009 Respiratory protective devices. Filtering half masks to protect against particles Requirements, testing, marking
EN 14594:2018 Respiratory protective devices. Continuous flow compressed air line breathing devices. Requirements, testing and marking
EN 12941:1998+A2:2008 Respiratory protective devices. Powered filtering devices incorporating a helmet or a hood. Requirements, testing, marking
EN 143:2000 Respiratory protective devices. Particle filters. Requirements, testing, marking
Directive 98/24/EC on the protection of the health and safety of workers from the risks related to chemical agents at work
Directive 2004/37/EC on the protection of workers from the risks related to exposure to carcinogens o mutagens at work
Directive 2017/2398 Amending Directive 2004/37/EC on chromium VI exposure limit
Directive 2017/164/EU indicative occupational exposure limit values (for nitrogen oxides)
Directive 2019/130 Amending Directive 2004/37/EC on the protection of workers from the risks related to exposure to carcinogens or mutagens at work

(Contd. on page 11)

EU

Page 11/13

# Safety data sheet according to 1907/2006/EC, Article 31


Printing date 17.02.2022

Version number 42

Revision: 05.05.2021

Trade name: Union AIMg 4,5 Mn

		Welding Exposure Scenario WES - ENGL Doc -5-2021	
Europea	n Welding Association	Page 5 of 6	
Use Descrip	tor System according to REAC	1 Regulation	
REACH use chain comm		eveloped by $ECHA^1$ to facilitate chemical risk assessment and supply	
such, they a		on-intentional byproducts generated during welding operations. As es or mixtures under REACH definition. They are not intended to be	
	ccupational exposure to weldi and mixtures regulated by REA	ng fumes and gases may represent a risk similar to the ones of the CH.	
the health a	cation of hazards, the evaluatio Ind safety can be implemented has been applied to welding fu		
		tage. The EWA welding consumable manufacturers define 2 life cycle b) the application at an industrial site.	
Sec Pro Pro Art	REACH uses five descriptors: ctor of use (SU), (NOTE: previou ccess category (PROC), oduct category (PC), icle category (AC) and vironmental release category (E	sly listed SU3 and SU10 have been removed by ECHA <sup>1</sup> ]	
to describe	identified uses.		
Manufactur SU Industrial ar	nd Professional welding:	OC21 PROC22 PROC23 PROC24 PROC25 ERC 2 ERC3 AC7	
SU14	Manufacture of basic metal	ROC22 PROC23 PROC24 PROC25 ERC5 ERC8c ERC8f AC1 AC2 AC7	
SU15 SU17 PC7	Manufacture of fabricated r General manufacturing, e.g Base metals and alloys	netal products, except machinery and equipment machinery, equipment, vehicles, other transport equipment	
PC38 PROC5 PROC21 PROC22			
PROC23 PROC24 PROC25	Open processing and transf	er operations with minerals/metals at elevated temperature ork-up of substances bound in materials and/or articles	
ERC2 ERC3 ERC5	Formulation of preparation Formulation into solid matr	5	
AC1 AC2	Vehicles	liances, electrical/electronic articles	
AC7			



Page 13/13

## Safety data sheet

according to 1907/2006/EC, Article 31

Printing date 17.02.2022

Version number 42

Revision: 05.05.2021

Trade name: Union AIMg 4,5 Mn

(Contd. of page 12) H261 In contact with water releases flammable gases. Department issuing SDS: R&D · Contact: Helena Stabel Abbreviations and acronyms: NCEC - National Chemical Emergency Centre (=Carechem24) ADR: Accord relatif au transport international des marchandises dangereuses par route (European Agreement Concerning the International Carriage of Dangerous Goods by Road) IMDG: International Maritime Code for Dangerous Goods IATA: International Air Transport Association GHS: Globally Harmonised System of Classification and Labelling of Chemicals EINECS: European Inventory of Existing Commercial Chemical Substances ELINCS: European List of Notified Chemical Substances CAS: Chemical Abstracts Service (division of the American Chemical Society) TRGS: Technische Regeln für Gefahrstoffe (Technical Rules for Dangerous Substances, BAuA, Germany) PBT: Persistent, Bioaccumulative and Toxic vPvB: very Persistent and very Bioaccumulative Flam. Sol. 1: Flammable solids - Category 1 Pyr. Sol. 1: Pyrophoric solids – Category 1 Water-react. 2: Substances and mixtures which in contact with water emit flammable gases - Category 2 FU